

# **CRYST ROOF®**

Article-No.: 05300

# ELASTIC WATERPROOFING ROOF COAT

# DESCRIPTION

CRYST ROOF<sup>®</sup> is a one-component, elastic, sealing coat with a very high special polymers content that penetrates into the pores of the substrate and seals it permanently to provide a flexible waterproofing of roof buildings. It presents excellent bonding and elongation characteristics, which makes it an ideal solution for surface waterproofing under temperature variations, crack bearing, and moving surfaces.

# FEATURE AND BENEFITS

- Environmentally friendly.
- Ideal for waterproofing, UV rays stable, and external conditions resistant.
- save energy costs by reflecting sun rays and heat away from the building.
- Suitable to be coated over leaking finished roofs.
- Self priming, non-toxic, and non flammable.
- Seamless and jointless coating when applied continuously.
- High durability to long term weathering effect.
- High adhesion on many substrates including concrete, cement mortars, and screeds propertiese.
- One-component product, only water needs to be added.
- Excellent elongation and crack bridging properties.
- Excellent abrasion resistance and mechanical.

# FIELD OF APPLICATION

- Uses for all types of waterproofing and protective coating for roofs, terraces, and balconies.
- Waterproofing and protective coating for most building substrates such as concrete, cement screeds, brick, plastering, tiles, PU foam, and primed steel.
- Decorative overlay and over existing terrazzo tiles.
- Waterproofing of corrugated sheets and sloped roofs.

## **MATERIAL PROPERTIES**

Form: powder	
Appearance: light grey / white	
Bulk Density: approx.1.4 g/cm <sup>3</sup>	
Application temperature: +8°C up to +40°C	
Pot life (30°C): approx. 45 minutes, depend on temperature	

## **TECHNICAL DATA**

Tensile adhesion Strength:2 N/mm2Crack bridging ability: $\geq 2 mm$ 

## **DIRECTION FOR USE**

#### Surface preparation:

The surface must be mineral, dry, or light humid, sound, and clean. Bonding inhibiting agents such as grease, oil, formwork oil, and all loose particles and dust must be removed before the application of CRYST ROOF<sup>®</sup>. The damaged area like cracks, holes have to be chased out, and filled with CRYST MORTAR. The small voids can be repaired with CRYST roof<sup>®</sup> with adjustable water (reduce the water to be thick slurry).

# **TECHNICAL DATA SHEET**



#### **Product mixing:**

Add clean water into a clean mixing bucket and mechanically stir mixing machine slowly and mix in as much CRYST ROOF<sup>®</sup> until a lump free, homogenous mass with either a slurry or sprayable consistency is achieved. If the mixture starts to set, do not add more water; simply re-stir to restore workability. Only mix as much material as can be used within 30 minutes. Allow to stand for at least 3 minutes then briefly remix.

#### Mixing ratios:

Mix 20 Kg of CRYST ROOF® to 5.5 - 6 liters clean water.

#### Application:

Dampen surface with clean water just prior to product application. Uniformly apply the first coat with a short bristle brush or roller, making sure to fill in all surface pores and voids. For maximum waterproofing performance, apply a second coat after first coat has dried for 2 hours. The maximum recommended thickness for these methods of application is 1 mm per layer.

Brush application: Apply CRYST ROOF<sup>®</sup> In 2 directions (diagonally opposite / crosswise).

Roller application: Apply CRYST ROOF® exerting good and even pressure onto the substrate.

**Spray application:** CRYST ROOF<sup>®</sup> can be applied with suitable spray equipment than dependent on the exposure conditions, spray apply one or two coats in a circular movement.

#### **Application rates:**

**Vertical & Horizontal surfaces:** CRYST ROOF<sup>®</sup> at 1 kg/m<sup>2</sup> per coat applied by roller, brush or spray.

**Construction joints:** CRYST ROOF<sup>®</sup> at (1.25 kg/m<sup>2</sup>) per coat applied by brush in concrete Joints, pipes or anywhere else in the structure must also be sealed and made watertight.

#### NOTES:

- Do not Apply CRYST ROOF<sup>®</sup> for thick coatings (more than 2 mm per coat).
- At right angles, pipe penetrations, drainages, it is recommended to embed a fibre mesh sandwich between the coatings.
- > Allow at least 48 hours to cure before subjecting to foot traffic.
- > Protect from rain for at least 24–48 h after application.
- > Clean all tools immediately with water after use.
- > To fully activate the material may require 3 days.
- Store in a dry environment.
- ➢ For more detailed instructions, or information concerning the compatibility of the CRYSTARM<sup>®</sup> application contact the CRYSTARM<sup>®</sup> Technical Department or your local CRYSTARM<sup>®</sup> representative

## **RECOMMENDED TOOLS**

Brush, roller, gloves, safety glasses, and stirring mixing machine.

#### PACKAGING

CRYST ROOF<sup>®</sup> is available in 20 kg bags or pails.

## **BASIS OF PRODUCT DATA**

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.



# **STORAGE & SHELF LIFE**

Keep CRYSTARM products must be stored dry and at a temperature of no less than 45°F (7°C). 12 months is the maximum shelf life when stored under proper conditions in original unopened packaging.

# SAFETY HANDLING

CRYST ROOF<sup>®</sup> is made of Portland cement and silica sand may irritate your eyes and skin. Take adequate precautions, such as wearing protective gloves and using breathing apparatus if applied in enclosed environments. If contact is made, flush areas with lots of water. For further information please refer to Safety Data Sheet. KEEP OUT OF REACH OF CHILDREN.

## CRYSARM<sup>®</sup>

Drescherstraße 53, D-71277 Rutesheim, GERMANY TEL +49 (0) 7152 300 330 FAX +49 (0) 7152 300 355 email info@ crystarm.com www.crystarm.com

CRYSTARM <sup>®</sup>		
Drescherstraße 53, D-71277 Rutesheim		
EN 1542, EN 1062-7		
CRYST ROOF®		
Coating for protection and re	epair of concrete	
structures protection against ingress (Class 2.2 (C))		
Tensile adhesion strength:	≥ 2.0 N/mm²	
Crack-bridging:	≥ 2 mm	
Reaction to fire:	Class A1	
Coefficient of thermal expansion	NPD	
Release of dangerous substances	NPD	
Water vapour permeability:	Class I < 5 m	
Capillary water absorption		
and water permeability:	≤0,1 kg/m² x h0,5	
Impermeability to water under		
pressure (5 bar for 7 days of		
positive & negative):	No penetration	
Reaction to fire:	NPD	
Dangerous substances:	NPD	

( (

WARRANTY: The Manufacturer warrants that the products manufactured by it conform to the formulation standards contained in all components in their proper proportion and are free from material defects. If any of the products are found to be defective the subsequent liability to The Manufacturer shall be limited only to the replacement of the product proven to be defective and shall not be liable for any other claim or for incidental or any consequential damages that may arise directly or indirectly with the said defective product. The user shall determine the suitability of the product for its intended use and the user assumes all liability in connection therein and the manufacturer shall not be liable save for terms of this warranty.

# SMART WATERPROOFING SYSTEM

# **TECHNICAL DATA SHEET**